

PET-G

PET-G is a strong, high clarity, odor neutral and easy to print filament for 3D printing. These characteristics, together with the high impact strength, excellent flexibility and practically no shrinkage make PET-G an excellent material which combines the advantages of both PLA and ABS. In short, PET-G has many great features and is the perfect addition to any filament assortment.


Material features:

- High clarity
- Strong & Flexible
- Almost no “warping”
- Food Contact Acceptable
- Odor neutral printing



Colours:

PET-G is available from stock in 19 colours. Other colours on request



Packaging:

PET-G is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Filament specs.

Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties

Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,27 g/cc
MFI 190°C/2,16 kg	ISO 1133	6,4 g/10 min
Tensile strength at yield	ISO 527	50 MPa
Elongation strain at yield	ISO 527	6%
Elongation strain at break	ISO 527	23%
Tensile (E) modulus	ISO 527	2020 MPa
Flexural modulus	ISO 178	2050 MPa
Flexural strength	ISO 178	69 MPa
Impact strength - Charpy method 23°C	ISO 179 1eA	8,1 kJ/m ²
Rockwell hardness	ASTM D785	105
Moisture absorption	ISO 62	1104 ppm
Printing temp.	Internal method	240±10°C
Heat deflection temp.	ASTM 648	70°C
Transparency	ASTM D1003	90%

Additional info:

Low hygroscopic, printable without drying, but drying improves printing performance. Recommended temperature for heated bed is ≥70°C. Adhesion is possible on different surfaces. PET-G can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/ recycling practices of the materials for the intended application.