

WEALA GLITTER

PLA GLITTER is a highly aesthetical PLA based filament with sparkling flakes inside. Slightly modified, the filament retains the typical features of PLA, but is tougher and less brittle. Polylactic acid is one of the most popular materials for 3D printing. Because of the translucency of PLA combined with the flakes, the colour saturation can be increased by increasing wall thickness.

Material features:

- Beautiful sparkling effect
- Layers are not visible
- Tougher and less brittle compared to regular PLA
- Easy to print
- Low warping
- Limited smell
- Not abrasive

Colours:

PLA GLITTER is available from stock in twelve colours. Other colours on request mgymgo mrd mgr mbu msi mbr mca mor mbl mle mpu

Packaging:

PLA GLITTER is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.



3 walls 2 walls

Filament specs.		
Size	Ø tolerance	Roundness
1,75mm	± 0,05mm	≥ 95%
2,85mm	± 0,10mm	≥ 95%

Material properties		
Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,24 g/cc
MFR 210°C/2,16 kg	ISO 1133	9,56 gr/10 min
Tensile strength at yield (MPa)	ISO 527	70 MPa
Strain at yield	ISO 527	5%
Strain at break	ISO 527	20%
E-Modulus	ISO 527	3120 MPa
Impact strength - Charpy method 23°C	ISO 179	3,4 kJ/m2
Moisture absorption	ISO 62	1968 ppm
Printing temp.	Internal method	205±10°C
Melting temp.	ISO 11357	115±35°C
Vicat softening temp.	ISO 306	60°C
Glass transition temp.	ISO 11357	57°C

Additional info:

Due to its low tendency to warp PLA GLITTER can also be printed without a heated bed. If you have a heated bed the recommended temperature is ≤60°C. PLA GLITTER can be used on all common desktop FDM or FFF technology 3D printers. It is recommended to purge the nozzle after printing, to prevent build up of flakes for the next print.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

"The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information is accurate, correct, reliable or current. MCPP reserves the right to make any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and determining the safety, lawfulness, technical suitability, proprietary rights, and disposal/recycling practices of the materials for the intended application