

PC-ABS VO is a halogen free flame-retardant filament meeting the UL-94 VO standard. Even though the high content of PC, for superb interlayer adhesion and dimensional accuracy, PC-ABS VO still prints at ABS-like temperatures. A perfect solution in case self extinguishing properties are required for your printed objects.

#### **Material features:**

- Flame retardant (UL-94 V0)
- Halogen free

Power to Perform

- Superb interlayer adhesion
- High surface gloss
- Stable printing process
- 'Yellow card' certified

### Colours:

PC-ABS V0 is available from stock in 1 colour. Other colours on request

# bk1

## Packaging:

PC-ABS VO is available in nearly any type of packaging and labelling. Ask our team to help you customizing your product.

Roundness
≥ 95%
≥ 95%

Material properties		
Description	Testmethod	Typical value
Specific gravity	ISO 1183	1,17 g/cc
MFI 260°C/5 kg	ISO 1133	43 g/10min
Tensile strength at yield	ISO 527	60 MPa
Elongation strain at break	ISO 527	>50%
Tensile (E) modulus	ISO 527	2850 MPa
Flexural Strength	ISO 178	110 MPa
Flexural Modulus	ISO 178	2800 MPa
Impact Strength - Charpy method 23°C Notched	ISO 179 1eA	42,5 kJ/m2
Printing temp.	Internal method	270±10°C
Vicat Softening Temp.	ISO 306	104°C
Flammability-rating	UL-94	V0

### Additional info:

Recommended temperature for heated bed is ≥100°C. We recommend kapton and / or pva glue stick for adhesion. PC-ABS V0 can be used on all common desktop FDM or FFF technology 3D printers.

Storage: Cool and dry (15-25°C) and away from UV light. This enhances the shelf life significantly.

"The values presented in this publication are based on MCPP's knowledge and experience and are intended for reference purposes only. While MCPP has made every reasonable effort to ensure the accuracy of the information in this publication, MCPP does not guarantee that it is error-free, nor does MCPP make any other representation, warranty or guarantee that the information contained herein, including, but not initiate to, any adjustments to the information contained herein at any time without notice. MCPP expressly disclaims warranties of any kind regarding the information contained herein, including, but not limited to, any warranties of merchantability or fitness of a particular purpose, use or application. MCPP shall not be liable for any damage, injury or loss induced from the use of MCPP's products in any application. Each user should thoroughly review this publication before selecting a product and, in view of the many factors that may affect processing and application of the product, each user should carry out their own investigations and tests and deterdy, lawfuncting practices of the materials for the intended application."

